

AQUENCE FB 3558

Known as: Adhesin 3558
August 2019

Description:

Trouble shooting grade Acrylic/EVA blend for paper converting applications where good adhesion and flexibility are the prime requirements – High speed packet, glue-lap, case & carton making, window/foil film to paper & board. Good adhesion to paper coatings, most films and foils.

This adhesive is gluten allergen free.

Typical Properties:

Appearance:	White
Odour:	Low when wet, dries odourless
Viscosity:	Approx. 3500 cP at 23°C
Solids:	Approx. 54%
pH:	Approx. 5.0

Directions for Use:

AQUENCE FB 3558 is supplied ready to use and generally applied by direct transfer from roller, wheel and rotary stencil applicators. This adhesive has excellent adhesion to difficult surfaces such as lacquered, printed and laminated boards. This adhesive features excellent machining properties. The final bond improves up to one week. The final bond has good heat and humidity resistance. Incompatible with some metals resulting in gelling. Stainless steel pipes and fittings should be used with this product.

Supplementary Products:

Previously called Adhesin 3558.

If a lower viscosity product is required Aquence FB 3557 - 800cP at 23°C.

Clean Up:

With water whilst wet.

Storage and Handling:

Please read the Material Safety Data Sheet for this product BEFORE use.

Product should be stored between 15°C and 30°C on a wooden pallet and kept from freezing. Rotate stock using oldest material first. Keep stock covered to prevent drying out and contamination. Do not mix with other adhesives. Supplied ready for use but can be diluted with water if required.

Please ensure that products classed as a dangerous good are stored in compliance with the applicable regulations.

Shelf Life:

Best used within 6 months from date of manufacture when stored under the above conditions in the original unopened containers.

Last Updated: 26-08-2015

DISCLAIMER

Any information given is, to the best of our knowledge, the best currently available, with respect to our products and their use, but it is subject to revision as additional knowledge and experience is gained. Such information is offered as a guideline for experimentation only and is not to be construed as a representation that the material is suitable for any particular purpose or use. Customers are encouraged to make their own enquiries as to the material's characteristics and, where appropriate, to conduct their own tests in the specific context of the material's intended use. This information is not a license to operate under nor is it intended to suggest infringement of any patent. We guarantee a uniform quality standard for this product. The only conditions and warranties accepted by Henkel in relation to this product or process are those implied by either Commonwealth or State statutes.

All Technical Data Sheets are uncontrolled documents, copies are not automatically updated